

THIN-TOP SUPREME

ONE PART, MODIFIED DECK RESURFACER

DESCRIPTION

THIN-TOP SUPREME is a latex and microsilica modified cementitious mortar designed for use as a floor or deck topping at thicknesses of 1/16" to 3/8" (1.6 mm to 10 mm). This product is a one part formula which incorporates powder latex technology. It provides excellent durability under freeze/thaw cycling as well as protection against ingress by water, de-icing salts and corrosion. THIN-TOP SUPREME offers normal set times and a mid-range slump for easy workability.

PRIMARY APPLICATIONS

- Parking decks
- Pavements
- Joints
- Marine structures
- Curbs and gutters
- Ramps
- Floors
- Walkways

FEATURES/BENEFITS

- Provides a strong, wear resistant thin overlay
- Excellent durability under freeze/thaw cycling
- Contains an integral corrosion inhibitor
- Excellent bond to concrete and steel
- Resists penetration of water and de-icing salts for good substrate protection
- Suitable for both interior and exterior use
- Consistent working time in cold & hot weather
- ▲ Can contribute to LEED points

TECHNICAL INFORMATION

Typical Engineering Data**

Compressive Strength ASTM C 109, 2" (50 mm) cubes @ 2.9 qts (2.7 L)/50 lb (22.7 kg) bag.

Age	Strength
1 day.....	3,000 psi (20.7 MPa)
7 days.....	5,800 psi (40.0 MPa)
28 days.....	7,200 psi (49.6 MPa)
56 days.....	8,000 psi (55.1 MPa)

Flexural Strength ASTM C 348

1 day.....	700 psi (4.8 MPa)
3 days.....	800 psi (5.5 MPa)
28 days.....	1,000 psi (6.9 MPa)
56 days.....	1,200 psi (8.2 MPa)

Linear Shrinkage ASTM C 157 50% RH @ 73°F (23°C)

3 days.....	-0.02%
7 days.....	-0.05%
14 days.....	-0.08%
28 days.....	-0.09%
56 days.....	-0.09%

Tensile Bond Strength

Appearance: THIN-TOP SUPREME is a free flowing powder as packaged. After mixing and placing, the color may initially appear darker than the surrounding concrete. The color will lighten up substantially as it cures and dries out, however, it may always appear somewhat darker than the surrounding concrete.

PACKAGING/YIELD

THIN-TOP SUPREME is packaged in 50 lb (22.7 kg) moisture resistant bags. Yield: 0.45 ft³/bag (0.013 m³) when mixed with 3 qts (2.8 L) of water. Typical water requirement is 2.75 to 3.5 qts (2.6 to 3.3 L)/bag. A unit of material may be extended with 15 lb (6.8 kg) of 3/8" (9.5 mm) pea gravel. This will yield 0.53 ft³ (0.014 m³). Product strength may be reduced 10 to 15% with aggregate extension.

CAN A23.2-6B (28 days..... Greater than concrete

Bond Strength ASTM C 882 (modified)

1 day.....	1,000 psi (6.9 MPa)
7 days.....	2,100 psi (14.5 MPa)
28 days.....	2,500 psi (17.2 MPa)

Sulfate Resistance ASTM C 1012

7 days.....	+0.019%
28 days.....	+0.024%
56 days.....	+0.024%

Chloride Permeability ASTM C 1202

7 days.....	7,000 coulombs
28 days.....	2,000 coulombs
56 days.....	1,500 coulombs

Freeze/Thaw Resistance ASTM C 666 Procedure A

500 cycles 100% relative dynamic modulus

Working Time 30 to 40 minutes

Initial Set 1 to 1.5 hours

Final Set 3 hours

Unit Weight..... 127 lb/ft³ (2036 kg/m³)



The Euclid Chemical Company

19218 Redwood Rd. • Cleveland, OH 44110
Phone: [216] 531-9222 • Toll-free: [800] 321-7628 • Fax: [216] 531-9596
www.euclidchemical.com

An **RPM** Company



SHELF LIFE

2 years in original, unopened package.

COVERAGE

21.5 ft² @ 1/4" thickness (1.95 m² @ 6.3 mm).

DIRECTIONS FOR USE

Surface Preparation: Concrete surfaces must be structurally sound, free of loose or deteriorated concrete and free of dust, dirt, paint, efflorescence, oil and all other contaminants. Mechanically abrade the surface to achieve a surface profile equal to CSP 5-7 in accordance with ICRI Guideline 310.2. Properly clean profiled area.

Priming: Clean and prime exposed steel with DURALPREP AC. Concrete should be primed with a spray or brush coat of DURALPREP AC. Alternately, a Saturated Surface Dry (SSD) concrete surface can be primed with a scrub coat of THIN TOP SUPREME. The repair must be made before the scrub coat dries out.

Mixing: Single bags may be mixed with a drill and "jiffy" mixer. Use a paddle type mortar mixer for large jobs. All material should be in the proper temperature range of 60°F (15°C) to 90°F (32°C). Add the appropriate amount of water 2.75 to 3.5 qt (2.6 to 3.3 L)/bag for the batch size and then add the dry product. Mix for 3 to 5 minutes.

Placement: Discharge material from mixer immediately and place on to floor. For patching, spread with a trowel, come-a-long, or square tipped shovel to a thickness that matches the surrounding concrete. Apply by hand troweling. On large areas, use screed strips with vibratory screeding to level.

Finishing: This product is designed for finishing with a float or broom appearance. Do not add additional water to the surface during the finishing operation; use EUCOBAR finishing aid. For a hard, flat troweled surface, delay finishing until the product is near final set (approx. 3 hours) to reduce the risk of blistering during troweling.

Curing and Sealing: Proper curing procedures are important to ensure the durability and quality of the repair. To prevent surface cracking, cure the material with a high solids curing compound, such as SUPER AQUA-CURE VOX or SUPER DIAMOND CLEAR VOX. Note: **Do not use a solvent based curing compound on this product.** If a curing compound is not desired, cover with polyethylene for a minimum of three (3) days. **Do not wet cure.** Always re-establish floor and slab joints when using this product as an overlay.

CLEAN-UP

Clean tools and equipment with water before the material hardens.

PRECAUTIONS/LIMITATIONS

- Do not wet cure.
- Do not allow repairs to freeze until the material has reached a minimum of 1000 psi (7 MPa) compressive strength.
- Use only potable water for mixing.
- Do not add admixtures or sand.
- Do not use material at temperatures below 45°F (7°C) or above 100°F (38°C).
- No heavy traffic until the product has cured.
- Mixing partial bags may yield variable results, always mix full units.
- Do not use a solvent based curing compound on this product.
- Store product in a dry place.
- For repairs and toppings deeper than 3/8" (9.5 mm), use CONCRETE-TOP SUPREME.
- In all cases, consult the Material Safety Data Sheet before use.

Rev. 10.09

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.